

## IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A gray soda-lime silicate glass composition, ~~characterized in that it comprises~~ comprising the following coloring agents with contents varying within the following weight limits:

Fe <sub>2</sub> O <sub>3</sub> (total iron)	0.01 to 0.14%
CoO	40 to 150 ppm
NiO	200 to 700 ppm

the NiO/CoO weight ratio being between 3.5 and 6 and the glass having an overall light transmission (TL<sub>D65</sub>) under illuminant D<sub>65</sub> of between 20 and 60% measured for a thickness of 6 mm.

Claim 2 (Currently Amended): The composition as claimed in claim 1, ~~characterized in that~~ wherein the light transmission TL<sub>D65</sub> is between 35 and 50%, preferably between 35 and 45%.

Claim 3 (Currently Amended): The composition as claimed in ~~either of claims 1 and 2, characterized in that~~ claim 1, wherein the glass has the following chromatic coordinates measured under illuminant D<sub>65</sub>:

L*	varies from 50 to 85, preferably 65 to 75;
a*	varies from - 4 to 0; and
b*	varies from - 5 to + 3.

Claim 4 (Currently Amended): The composition as claimed in ~~one of claims 1 to 3,~~  
~~characterized in that~~ claim 1, wherein the NiO/CoO weight ratio is between 3.5 and 4.5 and  
in that  $b^*$  is between -5 and -1.

Claim 5 (Currently Amended): The composition as claimed in ~~one of claims 1 to 3,~~  
~~characterized in that~~ claim 1, wherein the NiO/CoO weight ratio is between 5 and 6 and in  
that  $b^*$  is between -1 and +2.

Claim 6 (Currently Amended): The composition as claimed in ~~one of claims 1 to 5,~~  
~~characterized in that it~~ claim 1, wherein the composition comprises the following colorants in  
contents that vary within the following weight limits:

Fe <sub>2</sub> O <sub>3</sub> (total iron)	0.07 to 0.12%;
CoO	70 to 90 ppm;
NiO	300 to 500 ppm.

Claim 7 (Currently Amended): The composition as claimed in ~~one of claims 1 to 6,~~  
~~characterized in that~~ claim 1, wherein the redox varies from 0.1 to 0.3, preferably between  
0.15 and 0.28.

Claim 8 (Currently Amended): The composition as claimed in ~~one of claims 1 to 7,~~  
~~characterized in that it~~ claim 1, wherein the composition contains no Se and no MnO<sub>2</sub>.

Claim 9 (Currently Amended): The composition as claimed in ~~one of claims 1 to 8,~~  
~~characterized in that it~~ claim 1, wherein the composition consists of a glass matrix that  
comprises the following constituents (in percentages by weight):

SiO <sub>2</sub>	64-75%
Al <sub>2</sub> O <sub>3</sub>	0-5%
B <sub>2</sub> O <sub>3</sub>	0-5%
CaO	5-15%
MgO	0-10%
Na <sub>2</sub> O	10-18%
K <sub>2</sub> O	0-5%
BaO	0-5%.

Claim 10 (Currently Amended): A glass sheet formed by the float process on a bath of molten metal, or by rolling, with a chemical composition as defined by ~~any one of claims 1 to 9~~ claim 1.

Claim 11 (Currently Amended): A thermally toughened glass sheet ~~having a~~ comprising the composition as claimed in ~~any one of claims 1 to 9~~ claim 1 and having the following chromatic coordinates measured under illuminate D<sub>65</sub> for a thickness of 6 mm:

a\* varies from - 2 to 0;

b\* varies from - 10 to + 2, preferably -4 to 0.

Claim 12 (Currently Amended): The glass sheet as claimed in ~~either of claims 10 and 11, characterized in that it~~ claim 10, wherein the glass sheet has a thickness of between 2 and 19 mm.

Claim 13 (Currently Amended): The glass sheet as claimed in ~~one of claims 10 to 12,~~  
~~characterized in that it furthermore includes~~ claim 10, wherein the glass sheet further  
comprises at least one film of at least one metal oxide for reflecting infrared radiation.

Claim 14 (Currently Amended): ~~Glazing, especially for buildings, characterized in~~  
~~that it~~ A glazing, wherein the glazing comprises at least one glass sheet as claimed in ~~one of~~  
~~claims 10 to 13~~ claim 10.

Claim 15 (New): The thermally toughened glass sheet as claimed in claim 11,  
wherein the thermally toughened glass sheet has a thickness of between 2 and 19 mm.

Claim 16 (New): The thermally toughened glass sheet as claimed in claim 11,  
wherein the thermally toughened glass sheet further comprises at least one film of at least one  
metal oxide for reflecting infrared radiation.

Claim 17 (New): A glazing, wherein the glazing comprises at least one glass sheet as  
claimed in claim 11.

Claim 18 (New): A building glazing comprising the glass sheet as claimed in claim  
10.

Claim 19 (New): A building glazing comprising the thermally toughened glass sheet  
as claimed in claim 11.